CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON FINE AGGREGATES

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D.B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	04/05/2022
Specific Gravity	**2.59**
Technical Reference	IS : 2386(Part I)-1963 (Reaffirmed 2016), IS : 2386 (Part III)-1963 (Reaffirmed 2016)

Sample	IS Sieve designation (mm)	Sieve Analysis (% Passing IS Sieve)	Grading Requirement as per IS 383 : 2016				Grading Zone	Remarks
			ZONE-I	ZONE-II	ZONE-III	ZONE-IV		
Crushed Stone Sand	10	**100**	100	100	100	100	II	Satisfies the requirement
	4.75	**98.2**	90-100	90-100	90-100	95-100		
	2.36	**89.4**	60-95	75-100	85-100	95-100		
	1.18	**77.7**	30-70	55-90	75-100	90-100		
	0.6	**55.1**	15-34	35-59	60-79	80-100		
	0.3	**28.8**	5-20	8-30	12-40	15-50		
	0.15	**17.8**	**0-20***	**0-20***	**0-20***	**0-20***		

► ***For Crushed Stone Sand the permissible % passing on upper limit for 150μ IS Sieve is increased from 10 for Zone I,II,III & 15 for Zone IV, to 20%**

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D)
Quality Engineer

CIVIL TECH LA. BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

TEST ON CEMENT

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	04/05/2022
Grade & Brande	53

Tests	**Test Method As Per IS & Apparatus**		**Results**		**Requirements as per IS 12269:1987**	**Remarks**
	IS Code	**Method**	**Value**	**Unit**		
Initial Setting Time	**IS-4031 (Part-5) 1988**	VICAT	48	min	Not Less Than 30 Minutes	Satisfies Requirement
Final Setting Time	**IS-4031 (Part-5) 1988**	VICAT	487	min	Not More Than 600 Minutes	Satisfies Requirement
Soundness	**IS-4031 (Part-3) 1988**	LE-CHATELIER	3	mm	Not More Than 10 mm	Satisfies Requirement

Note:

1.The results relate only to the items tested.

2.Report shall not be reproduced except in full, without the written approval of the lab.

3.Any correction invalidates this report.

4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI SD)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON COARSE AGGREGATES 40mm ↓ Graded

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	04/05/2022
Specific Gravity	**2.62**
Water Absorption	**0.30%**
Technical Reference	IS : 2386(Part I)–1963 (Reaffirmed 2016), IS : 2386 (Part III)–1963 (Reaffirmed 2016)

IS Sieve Designation (mm)	Sieve Analysis (% Passing IS Sieve)	Grading Requirement as per IS 383 : 2016	Remarks
80	**100**	100	**Satisfies the requirement**
40	**97.8**	90-100	
20	**68.2**	30-70	
10	**34.2**	10-35	
4.75	**3.6**	0-5	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON COARSE AGGREGATES 20mm ↓ Graded

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	04/05/2022
Specific Gravity	**2.63**
Water Absorption	**0.31%**
Technical Reference	IS : 2386(Part I)-1963 (Reaffirmed 2016), IS : 2386 (Part III)-1963 (Reaffirmed 2016)

IS Sieve Designation (mm)	Sieve Analysis (% Passing IS Sieve)	Grading Requirement as per IS 383 : 2016	Remarks
40	**100**	100	**Satisfies the requirement**
20	**98.2**	90-100	
10	**53.9**	25-55	
4.75	**8.2**	0-10	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Yashaswini

(YASHASWINI S D)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON WET MIX MACADAM

Name & Address of the Customer	AEE,Yalahanka Division BBMP, Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	07/05/2022
Technical Reference	IS : 2386(Part I)-1963 (Reaffirmed 2016)

	Sample-1		
IS Sieve Designation (mm)	**% By Weight Passing IS Sieve as per MORTH (4th Revision) Table 400-11 for WMM**	**Actual % By Weight Passing IS Sieve**	**Remarks**
53	100	**100**	**Satisfies the requirement**
45	95-100	**97.1**	
22.4	60-80	**76.2**	
11.2	40-60	**58.3**	
4.75	25-40	**37.7**	
2.36	15-30	**28.5**	
0.6	8-22	**19.4**	
0.075	0-8	**6.9**	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Yashaswini S D

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON GRANULAR SUB BASE MATERIALS GRADING - V

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	07/05/2022
Technical Reference	IS : 2386(Part I)-1963 (Reaffirmed 2016)

IS Sieve Designation (mm)	% By Weight Passing IS Sieve as per MORTH (5th Revision) Table 400-1 for GSB Grading-V	Actual % By Weight Passing IS Sieve	Remarks
75	100	**100**	**Satisfies the requirement**
53	80-100	**89.2**	
26.5	55-90	**79.2**	
9.5	35-65	**62.3**	
4.75	25-50	**47.7**	
2.36	10-20	**18.6**	
0.85	2-10	**8.3**	
0.425	0-5	**4.3**	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

CIVILTECH LABS

RATE OF SPREAD OF TACK COAT

Name of the Client	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of Agency	Sri. M Ravish Kumar
Date of Testing	10/05/2022

Test No.	Area Tested	Rate of spread Kg/m²	As Per MORTH Table 500-5	Remarks
1	Rate of Spread Test conducted for every 500 m² from area 0 to 5000 m²	0.25	0.25 to 0.30 Kg/m²	Satisfactory
2		0.26		Satisfactory
3		0.25		Satisfactory

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.

Yashaswini S D
Quality Engineer

CIVIL TECH LAB'S BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

DETERMINATION OF BINDER CONTENT FROM BITUMINOUS PAVING MIXTURE FOR QUALITY CONTROL - BITUMINOUS MACADAM MIX-GRADE 2

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	10/05/2022
Technical Reference	ASTM: D2172/D2172M-17 - Test Method A - Centrifuge Extraction

Specification: As Per MORTH (4th Revision) Table 500-4 BM-Grade -2, Bitumen Content for BM Grade-2 is 3.3 % TO 3.5 %

Sl. No.	Description	Values
1	Weight of bituminous mixture before extraction test, W_1 g	**2000.0**
2	Total Weight of mineral aggregate obtained from centrifuge extractor, W_2 g	**1943.0**
3	Total weight of Bitumen extracted from the mixture, W_3 g = (W_1-W_2) g	**57.0**
4	Bitumen content in %, (W_3/W_1) %	**2.9**

Remarks	Satisfies the requirement

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON BITUMINOUS MACADAM MIX GRADE - 2

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	10/05/2022
Technical Reference	IS : 2386(Part I)–1963 (Reaffirmed 2016)

	Sample-1		
IS Sieve Designation (mm)	**% By Weight Passing IS Sieve as per MORTH (4th Revision) Table 500-4 for BM Grade-2**	**Actual % By Weight Passing IS Sieve**	**Remarks**
26.5	100	**100**	**Satisfies the requirement**
19	90-100	**98.2**	
13.2	56-88	**87.3**	
4.75	16-36	**32.5**	
2.36	4-19	**18.1**	
0.3	2-10	**8.6**	
0.075	0-8	**6.9**	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

GRADATION TEST ON BITUMINOUS CONCRETE MIX GRADE - 2

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	11/05/2022
Technical Reference	IS : 2386(Part I)-1963 (Reaffirmed 2016)

	Sample-1		
IS Sieve Designation (mm)	**% By Weight Passing IS Sieve as per MORTH (5th Revision) Table 500-17 for BC Grade-2**	**Actual % By Weight Passing IS Sieve**	**Remarks**
19	100	**100**	**Satisfies the requirement**
13.2	90-100	**98.2**	
9.5	70-88	**86.1**	
4.75	53-71	**65.5**	
2.36	42-58	**56.1**	
1.18	34-48	**43.2**	
0.6	26-38	**37.1**	
0.3	18-28	**26.3**	
0.15	12-20	**18.6**	
0.075	4-10	**9.2**	

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

DETERMINATION OF BINDER CONTENT FROM BITUMINOUS PAVING MIXTURE FOR QUALITY CONTROL - BITUMINOUS CONCRETE MIX-GRADE 2

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of the Agency	Sri. M Ravish Kumar
Date of Testing	11/05/2022
Technical Reference	ASTM: D2172/D2172M-17 - Test Method A - Centrifuge Extraction

Specification: As Per MORTH (5th Revision) Table 500-17, Minimum Bitumen Content for BC Grade-2 is 5.4%

Sl. No.	Description	Values
1	Weight of bituminous mixture before extraction test, W_1 g	2000.0
2	Total Weight of mineral aggregate obtained from centrifuge extractor, W_2 g	1883.0
3	Total weight of Bitumen extracted from the mixture, W_3 g = (W_1-W_2) g	117.0
4	Bitumen content in %, (W_3/W_1) %	5.9

Remarks	Satisfies the requirement

Note:

1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

(YASHASWINI S D.)
Quality Engineer

CIVIL TECH LABS BANGALORE

CIVIL TECH LABS

35/40, "Kaivara Krupa" First Floor, 38th 'A' Cross, II Main, 8th Block, Jayanagar,
BANGALORE-560070. Ph: 080 - 3500 2277, 3500 2275, Email: civiltechlabs@gmail.com

TEST REPORT

COMPRESSIVE STRENGTH TEST ON CONCRETE CUBES

Name & Address of the Customer	AEE,Yalahanka Division BBMP. Banglore.
Name of Work	**"Asphalting to road from D B Pura main road towards railway station (mini vidhanasodha road in Ward no-01"**
Name of Agency	Sri. M Ravish Kumar
Grade of Concrete	M-15
No. of cubes tested	3
Dimension of Specimen	150mmx150mmx150mm
Cross Sectional Area	22500 mm^2
Technical Reference	IS: 516-1959 (Reaffirmed 2013)

Sl. No.	Identification	Date of Casting	Date of Testing	Age at test (Days)	Weight (Kg)	Failure Load (KN)	Compressive Strength (N/mm^2)	Avg Compressive Strength (N/mm^2)
1	Covering slab	06/05/2022	12/05/2022	28	8.20	320	**14.22**	**13.85**
2					8.16	310	**13.78**	
3					8.18	305	**13.56**	

Note:
1. The results relate only to the items tested.
2. Report shall not be reproduced except in full, without the written approval of the lab.
3. Any correction invalidates this report.
4. The results are based on the test conducted on samples supplied by the customer.

Yashaswini SD
(YASHASWINI SD)
Quality Engineer

CIVIL TECH LABS BANGALORE